

BLENDCRETE

Description

ProSpec[®] BlendCrete is a one component, polymer modified, cement based concrete and masonry patching compound.

Features

- Fast setting, low slump repair mortar that can be trowelled, shaped and shaved after taking an initial set
- Easy shaping and molding
- One component incorporating water activated polymer system
- Integrated corrosion inhibitor
- Can be applied overhead and vertically without using expensive forming procedures
- Tenacious bond to substrates
- Interior/exterior
- Portland cement based
- Normal set time of 30 minutes; also available in 15 minute set time
- Available in 3 gray colors and one white color

Uses

- Used interior or exterior, above or below grade, on vertical, overhead and horizontal surfaces
- Suited for patching distressed horizontal, vertical and overhead surfaces including precast products, concrete pipe, curbs, sidewalks, bridges, panels and walls
- Used to fill honeycombs, form tie rise holes, spalls or irregularities due to misaligned forms or unconsolidated concrete

Technical Data

Working Time		Average Scaling Resistance (ASTM C 672-98)		
15 minutes at 70° F (21° C)		No. of cycles	Rating	Condition of surface
Set Time ASTM C 191 @ 70° F (21° C)		5	0	No scaling visible
Initial set	Approx. 20 min.	10	0	No scaling visible
Final set	Approx. 30 min.	15	0	No scaling visible
Compressive Strength ASTM C 928		20	0	No scaling visible
1 hour	1,500 psi (10.3 MPa)	25	0	No scaling visible
3 hours	2,500 psi (17.2 MPa)	Shear Bond Strength ASTM C 882		
1 day	3,000 psi (20.7 MPa)	1 day	1,035 psi (7.1 MPa)	
7 days	4,000 psi (27.6 MPa)	7 days	1,650 psi (11.4 MPa)	
28 days	5,000 psi (34.5 MPa)	Flexural Strength ASTM C 348		
Freeze/Thaw Resistance ASTM C 666 Method "B"		1 day	1,142 psi (7.9 MPa)	
After 300 cycles	1% loss due to slight scaling; no spalling	28 days	1,180 psi (8.1 MPa)	

Test results obtained under controlled laboratory conditions.
Reasonable variations can occur due to atmospheric and job site conditions.

BLENDCRETE

Preparation

Adjoining surfaces must be sound, clean, free of loose or damaged concrete, dust, dirt and other contaminants that will interfere with bond. Completely expose and clean all reinforcing steel, ensuring a minimum clearance of 3/4" (19 mm) behind reinforcing steel.

Perform reinforcing steel preparation in accordance with ICRI Technical Guidelines No. 03730. For best results patch area edges should be saw cut to a depth of 1/2" (13 mm). Abrade

concrete to obtain a rough surface promoting adhesion. The area should be saturated surface dry (SSD) with no standing water on the surface. The use of a vigorously scrubbed application of a no slump bond coat of BlendCrete or a bonding agent like ProSpec Acrylic Additive is recommended. This should be applied to all surfaces coming into contact with the patch. Do not allow bond coat to dry prior to the placement of the BlendCrete.

Refer to

- ICRI Guide No. 03732 [Selecting and Specifying Concrete Surface Preparation for Sealers, Coatings and Polymer Overlays](#)

Mixing

BlendCrete requires 4 to 5 quarts (3.8 to 4.7 L) of water per 50 lbs. (22.7 kg) of powder. Mix only the amount of material that can be placed in 15 minutes. Pour the required amount of potable water into a clean mixing container, then add the measured amount of BlendCrete while continuing to mix and blend thoroughly for 1-2 minutes to a lump free putty like consistency. Small amounts of BlendCrete can be mixed using a trowel or a 1/2" drill (400-600 r.p.m.) and paddle.

Extended Mix: To fill areas deeper than 2" (51 mm), add 15 lbs. (6.8 kg) of clean saturated surface dry 3/8" (10 mm) pea gravel to 50 lbs. (22.7 kg) of BlendCrete™. First mix the BlendCrete as outlined, then add the pea gravel and mix for 60 seconds. Total mixing time is not to exceed 2-3 minutes.

Do not over water, re-temper or over mix. Clean out the mixing container thoroughly after each batch to avoid getting hardened mortar into the next batch.

Application

Immediately apply the fresh mortar into the entire surface, forcing BlendCrete firmly into the previously prepared area insuring full contact with all bonding surfaces. Slightly overfill the area. After initial set, using a trowel, shave BlendCrete to the desired final profile, shaving the patch from the center towards the bond edge at the existing surfaces. A wet spray may be used for final shaping. In deeper areas additional

lifts can be made after the original patch has reached initial set. Score and roughen the original lift layer to improve bond between applications. BlendCrete can be placed in lifts up to 1" (25 mm) on vertical and overhead applications by holding the mortar in place until initial set has occurred.

BLENDCRETE

Clean Up

Use water to clean all tools immediately after use.

Best Performance

- Do not bridge moving cracks, control or expansion joints
- Protect from conditions that cause early water loss: such as wind, sunlight, heat, etc.
- The minimum applications thickness is 1/2" (12 mm)
- Do not overwork, re-temper, over water or add admixtures

Colors

White, gray color #0, gray color #2 and gray color #3

Curing

Cure in accordance with American Concrete Institute procedure number 308. Protect patch from high temperature, high wind, low humidity, and direct sun causing rapid drying, by covering with wet burlap or plastic for up to 24 hours. A water based curing compound can also be used.

Do not apply to frozen or frost covered areas. The minimum ambient and surface temperatures should be 40° F (4° C) at time of application. Hot weather and conditions above 80° F (27° C) will reduce working time and accelerate set, while cold temperatures below 60° F (16° C) will have a retarding effect.

Refer to

- ACI 305 [Standard on Hot Weather Concreting](#)
- ACI 306 [Standard on Cold Weather Concreting](#)
- ACI 308 [Standard Practice for Curing Concrete](#)

Coverage

One 50 lb (22.7 kg) bag yields approximately 0.48 ft.³ (0.01 m³)
With the addition of 15 lbs. (6.8 kg) of 3/8" (10 mm) pea gravel yield is approximately 0.60 ft.³ (0.02 m³)

Packaging

50 lbs. (22.7 kg) moisture resistant bag

Storage

Always keep in a cool dry place unexposed to sunlight.

Shelf Life

One year when stored properly in original unopened container.

BLENDCRETE

Caution

KEEP OUT OF REACH OF CHILDREN AND ANIMALS. WARNING!

Contains Portland cement and silica sand. May irritate eyes and skin. Avoid contact with eyes or prolonged contact with skin. In

case of contact, flush thoroughly with water. The wearing of gloves and safety goggles is recommended.

In case of eye contact, flood eyes with potable water and call physician. DO NOT RUB EYES.

Do not take internally. Crystalline silica sand may cause serious lung problems. Avoid breathing dust and wear a respirator in dusty areas.

Consult Material Safety Data Sheet for further information.

First Aid

Inhalation: Remove to fresh air
Eye Contact: Irrigate eye with water or consult physician if irritation persists.

Skin Contact: Washed exposed skin area with soap and water; consult a physician if irritation persists.

Ingestion: Immediately consult a physician.

LIMITED 1 YEAR WARRANTY FROM DATE OF MANUFACTURE: Bonsal American warrants that this product and the materials used therein meet or exceed the applicable standards listed and enforced at the time of manufacture. Bonsal American will replace any product or part which proves defective due to quality of ingredients used or due to the manufacturing process itself. This Warranty shall apply only if the product is used in strict accordance with applicable specifications and instructions provided by Bonsal American for its use, and Bonsal American shall not be liable otherwise. Replacement of any defective product, or, at Bonsal American's option, refund of the purchase of any defective product shall be the buyer's sole remedy under this Warranty, and Bonsal American shall in no event be liable for any damages in excess of the purchase price of the defective product. BONSAL AMERICAN SHALL IN NO EVENT BE LIABLE FOR ANY CONSEQUENTIAL, INCIDENTAL OR SPECIAL DAMAGES INCLUDING LOSS OF PROFITS OF ANY KIND. Product demonstrations are done for illustrative purposes only and do not constitute a warranty or warranty alteration of any kind. This Warranty constitutes the sole warranty given by Bonsal American in connection with this product. No modification of this Warranty in favor of any buyer shall be valid unless given in writing and signed by an officer of Bonsal American. Bonsal American has authorized no person to make or give any other warranties or representation, oral or written on its behalf. IN PARTICULAR, THERE ARE NO IMPLIED WARRANTIES, INCLUDING WITHOUT EXCEPTION WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.

ProSpec[®] is the registered trademark of Sakrete of North America.
8201 Arrowridge Blvd. Charlotte, NC 28273 • www.prospec.com • E-Mail: prospec@oldcastleapg.com