

STANDARD ASPHALT OVERDRIVE® DRIVEWAY SEALER

PRODUCT DATA

DESCRIPTION

An affordable, economical driveway sealer formulated to provide preventative driveway maintenance. Helps recoat and seal the driveway surface. Guards against damage caused by oil and gas stains, and daily wear-and-tear by resealing the driveway surface. Asphalt based formula.

USES

Preventative driveway surface maintenance. Use annually to recoat and seal the surface of your driveway and guard against damage caused by fluid spills (automobile oil and gas).

APPLICATION

Prepare the surface to receive the STANDARD ASPHALT OVERDRIVE® Coating by trimming grass, weeds, or bushes away from the driveway surface and sweep clean. Wash surface thoroughly with water. Remove oil or grease spots with detergent, and flush with clean water. Broom off puddles and remove any excess water. Surface can be damp prior to application. Fill cracks over 1/4" wide with OVERDRIVE Crack Filler or OVERDRIVE Rubberized Crack Filler.

After preparing surface, stir product thoroughly to assure even consistency. Do not dilute. Use directly from pail. Pour a ribbon of material across the surface. Using a suitable squeegee, roller, or brush work the product back and forth to allow sealer to penetrate the driveway surface and into fine cracks or pores. Apply the sealer in two thin coats. Never apply one thick coat, as material will not dry properly and may track.

First coat: Spread at the rate of 1 gallon per 80 to 100 square feet. This application varies dependent upon the texture of the surface. Allow at least 24 hours drying time before second application.


Second coat: Apply at same application rate in a pattern perpendicular to the first coat.

Clean tools thoroughly with water after use.

TYPICAL PHYSICAL PROPERTIES*

Weight Per Gallon, Lbs.	9.8
Cure Time (at recommended coverages)	4-8 hrs to set, 24-48 hrs to full cure weather depending

*All values stated as nominal



NOTES AND PRECAUTIONS

Do not use on concrete. For use only on asphalt surfaces. Newly laid asphalt pavement should cure for at least two months before Driveway Sealer is applied. Driveway Sealer is not to be used for repairing large cracks or broken pavement. DO NOT APPLY in damp weather, if rain is imminent, or if temperature is below 50°F. Protect from freezing.

Central District	220 West 4th Street, Joplin, Missouri 64801
Northeast District	4500 Tamko Drive, Frederick, Maryland 21701
Southeast District	2300 35th Street, Tuscaloosa, Alabama 35401
Southwest District	7910 South Central Expressway, Dallas, Texas 75216
Western District	5300 East 43rd Avenue, Denver, Colorado 80216

www.tamko.com

For Technical Services call 1-800-641-4691

800-641-4691
800-368-2055
800-228-2656
800-443-1834
800-530-8868

TAMKO®
ROOFING PRODUCTS